

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B65B 11/50	A1	(11) International Publication Number: WO 00/55046 (43) International Publication Date: 21 September 2000 (21.09.00)
<p>(21) International Application Number: PCT/EP00/01943</p> <p>(22) International Filing Date: 7 March 2000 (07.03.00)</p> <p>(30) Priority Data: 9906171.5 17 March 1999 (17.03.99) GB</p> <p>(71) Applicant (for AE AU BB CA CY GB GD GH GM IE IL KE LC LK LS MN MW NZ SD SG SL SZ TT TZ UG ZA ZW only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB).</p> <p>(71) Applicant (for all designated States except AE AU BB CA CY GB GD GH GM IE IL IN KE LC LK LS MN MW NZ SD SG SL SZ TT TZ UG ZA ZW): UNILEVER NV [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).</p> <p>(71) Applicant (for IN only): HINDUSTAN LEVER LIMITED [IN/IN]; Hindustan Lever House, 165/166 Backbay Reclamation, Mumbai 400 020, Maharashtra (IN).</p> <p>(72) Inventor: HARBOUR, Richard; Lever Brothers Ltd, P.O. Box 69, Port Sunlight, Wirral, Merseyside CH62 4ZD (GB).</p>		<p>(74) Agent: ELLIOTT, Peter, William; Unilever PLC, Patent Department, Colworth House, Sharnbrook, Bedford, Bedfordshire MK44 1LQ (GB).</p> <p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
<p>(54) Title: A PROCESS FOR PRODUCING A WATER SOLUBLE PACKAGE</p> <p>(57) Abstract</p> <p>A process for producing a thermoformed package comprises the steps of placing a first sheet of film over a forming die having at least one cavity, heating the film to mould the film into the at least one cavity thereby forming at least one recess in the film, placing a composition in the at least one formed recess, and sealing a second sheet of film across the at least one formed recess to produce at least one closed package. Once formed, the or each recess is substantially retained in its formed orientation by the application of a vacuum through the or each cavity.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

A PROCESS FOR PRODUCING A WATER SOLUBLE PACKAGE

5 Introduction

The invention relates to a process for producing a thermoformed package of the type comprising the steps of placing a first sheet of formable film over a forming die
10 having a cavity, moulding the film into the cavity thereby forming a recess in the film, placing a composition in the thus formed recess, and sealing a second sheet of film across the recess to close the package. In particular, the invention relates to such a process for producing a water-
15 soluble package containing a detergent composition.

Detergent compositions for the machine washing of laundry are provided in many forms. Probably the most prevalent form of laundry detergent is washing powder or granules. A
20 problem with the use of these forms of detergent is that the product needs to be dosed into the machine in such a way that the detergent is quickly and thoroughly dissolved in the wash water of the machine without coming into contact with the laundry in a solid form. In this regard many dosing
25 devices which overcome this problem have been proposed. One such device disclosed in European Patent Nos. 0 343 070 and 0 343 069 teaches the use of a flexible fabric sock which holds the particulate detergent in the machine, the fabric of the sock being permeable to water so as to allow water
30 enter the sock and carry the detergent out of the sock through the fabric walls in the form of an aqueous solution. More recently unit dose forms of detergent have been proposed in the form of compressed tablets of detergent
35 detergent tablets is that the tablets need to be strong enough to withstand storage and transport, yet weak enough to disintegrate and dissolve quickly in the washing machine.

- 2 -

A further problem is the need to prevent the tablets "posting" in the porthole and between the drums of conventional washing machines. More recently these problems have been overcome by the provision of detergent tablets
5 having specific chemical disintegrants which allow quick disintegration of the tablets in the aqueous environment of a washing machine, and by the provision of loosely fitting net bags which aid tablet disintegration and prevent "posting". However, as many of the current detergent tablets
10 contain bleach and other irritant substances, the problem of handling the tablets remains.

The provision of detergent compositions in water-soluble films has been known for some time. Most of the documents
15 relating to this subject describe water soluble film envelopes formed using a vertical form-fill-seal (VFFS) route. A problem with envelopes produced using this VFFS method is that, due to the constraints of the process, the resultant envelopes have seals which incorporate defined
20 weak points where the seals overlap at corners. This results in envelopes, which are easily corrupted as a result of impacts suffered during transport. In an attempt to overcome the problems associated with such VFFS envelopes, European Patent Application No. 0 608 910 describes thermoformed
25 water soluble packages for pesticidal compositions of the above mentioned type, which packages include a seal which does not have any angular intersections with itself. While this specification does provide a partial solution to the problem of weak seals, the thermoforming of water-soluble
30 films results in formed packages having many other weak points. Moreover, the packaging and transport of such packages subjects the formed packages to considerable impact forces. A further problem inherent with thermoforming processes, particularly when the thermoformed package is to

- 3 -

contain liquid, is contamination of the seal with liquid, resulting in poor sealing of the packages.

It is an object of the invention to overcome at least some
5 of the above problems.

Statements of Invention

According to the invention, there is provided a process for
10 producing a thermoformed package of the above-mentioned
type, the process being characterised in that, once formed,
the or each recess is substantially retained in its formed
orientation by the application of a vacuum through the or
each cavity. Ideally, the vacuum is maintained at least
15 until completion of the sealing step. In this way,
shrinkback of the formed recesses is minimised, thus
preventing spillage of the composition contained in the
formed recesses onto the sealing area of the film. The
extent of vacuum to be applied should be sufficient to
20 retain the formed recesses in their formed orientation
without unduly deforming or otherwise damaging the film. In
this regard the exact pressure to be applied is variable and
depends on the film being formed, the type of composition
being added to the recesses, and the temperature and
25 humidity of the forming environment. Typically however, a
vacuum of between 0.1 and 10 Bar will be used. The vacuum is
preferably applied through at least one aperture in the at
least one forming cavity. Ideally, the or each cavity will
include a plurality of apertures through which the vacuum is
30 applied. In one embodiment of the invention, the at least
one cavity may comprise a porous material through which the
vacuum may be applied.

Preferably, the or each cavity in the forming die has a
35 curved edge, wherein at least a portion of the curved edge

- 4 -

is formed from a resiliently deformable material. Ideally, a predominant portion, and most preferably a whole, of the curved edge is formed of a resiliently deformable material. In one embodiment of the invention, the curved edge
5 comprises an annular gasket of resiliently deformable material, which gasket is mounted in a circumferential groove around the or each cavity. In such a case, the gasket should be dimensioned such that, when mounted in the groove, an exposed surface of the gasket should be flush with a
10 surface of the cavity.

In a further aspect of the invention, the or each cavity is surrounded by a raised flange, wherein at least a portion, and ideally most or all, of the raised flange comprises
15 resiliently deformable material. In such a case, the curved edge and flange are preferably integrally formed. Thus, a single gasket preferably comprises the curved edge and the flange. In one embodiment of the invention, a ratio of a width of the flange to a minor diameter of the cavity is
20 between 1:50 and 1:10, preferably about 1:12.

The resiliently deformable material is preferably silicone rubber, however other suitable material performing the same function are envisaged.

25 In the thermoforming step of the process of the invention, the film is heated by a heating plate having at least one concave depression which in use overlies the at least one cavity, wherein the heating step involves the step of
30 bringing the film into intimate contact with the or each depression. The use of a heating plate having concave depressions ensures that the film when heated thermoforms uniformly which results in a package having less weak spots.

- 5 -

In one embodiment of the invention, intimate contact between the film and the concave depression is achieved by exerting a vacuum between the depression and the film. In this regard the depression may include holes through which the vacuum
5 may be pulled. Alternatively, the heating plate may comprise a porous material. When a vacuum is exerted in this manner, the vacuum should ideally comprise a pressure of up to 1 Bar, and preferably be less than 0.6 Bar. In an alternative embodiment of the invention, the film is forced into
10 intimate contact with the concave depression by blowing air against it. Typically the pressure of the blown air will be less than 5 Bar, preferably less than 3 Bar. The heating plate preferably has a temperature in the region of 100 to 120 degrees C, and ideally is approximately 110 degrees C.
15 Although the time the film contacts the heating plate depends to a large extent on the type of film used and the temperature of the heating plate, the time of contact between the film and the plate should be in the region 0.1 to 5 seconds, preferably 0.5 to 1 seconds, ideally
20 approximately 700 milliseconds.

In a particularly preferred embodiment of the invention, the at least one concave depression is circular. In such a case it is preferable that the ratio of the diameter of the
25 depression to the ratio of the depth of the depression is between 4:1 and 50:1, typically between 5:1 and 40:1, suitably between 7:1 and 30:1, ideally between 8:1 and 20:1. In a most preferable embodiment, the ratio is approximately 10:1. Thus in an embodiment of the invention which will be
30 described in further detail below, the concave depression is circular having a diameter of approximately 50 mm and a depth of about 5mm.

Ideally, the concave depression has a radiused edge.
35 Preferably the depression has a base having a radius of

- 6 -

curvature, wherein the ratio of the radius of curvature of the base to the radius of curvature of the edge is preferably between 5:1 to 1:1, and most preferably is about 2:1. Typically, a single plate may have a plurality of
5 concave depressions which in most instances will correspond to an equal number of cavities in the forming die.

In one embodiment of the invention the film is a water-soluble film. Ideally the package contains a liquid, gel or
10 other type of fluent composition. Preferably, the liquid comprises a detergent or any other type of active agent used in the machine washing of laundry or dishes. In another embodiment of the invention, the package contains a bathing or shower gel composition or any other type of personal care
15 composition.

DETAILED DESCRIPTION OF THE INVENTION

The invention will be more clearly understood from the
20 following description of some embodiment thereof, given by way of example only.

EXAMPLE

25 In this example a thermoforming process is described where a number of recesses are formed in a single sheet using a forming die having a plurality of cavities with dimensions corresponding generally to the dimensions of the packages to be produced. Further, a single heating plate is used for
30 moulding the film for all the cavities, and in the same way a single sealing plate is described.

A first sheet of polyvinyl alcohol film is drawn over a forming die so that the film is placed over the plurality of
35 forming cavities in the die. Each cavity is generally dome

- 7 -

shape having a round edge, the edges of the cavities further being radiussed to remove any sharp edges which might damage the film during the forming or sealing steps of the process. Each cavity further includes a raised surrounding flange. In order to maximise package strength, the film is delivered to the forming die in a crease free form and with minimum tension. In the forming step, the film is heated to 100 to 120 degrees C, preferably approximately 110 degrees C, for up to 5 seconds, preferably approximately 700 micro seconds. A heating plate is used to heat the film, which plate is positioned to superpose the forming die. The plate includes a plurality concave depressions which correspond to the recesses on the forming die. During this preheating step, a vacuum is pulled through the pre-heating plate to ensure intimate contact between the film and the pre-heating plate, this intimate contact ensuring that the film is heated evenly and uniformly (the extent of the vacuum is dependant of the thermoforming conditions and the type of film used, however in the present context a vacuum of less than 0.6 bar was found to be suitable) Non-uniform heating results in a formed package having weak spots. In addition to the vacuum, it is possible to blow air against the film to force it into intimate contact with the preheating plate.

The thermoformed film is thus moulded into the cavities forming a plurality of recesses which, once formed, are retained in their thermoformed orientation by the application of a vacuum through the walls of the cavities. This vacuum is maintained at least until the packages are sealed. Once the recesses are formed and held in position by the vacuum, the composition, in this case a liquid detergent, is added to each of the recesses. The fact that formed recesses are retained in their formed orientation by the vacuum substantially prevents the formed film shrinking, which if not prevented could result in some of the

- 8 -

composition in the recesses spilling out of the recess and onto that portion of film which overlies the sealing flange resulting in poor sealing. A second sheet of polyvinyl alcohol film is then superposed on the first sheet covering the filled recesses and heatsealed thereto using a heating plate. In this case the heat sealing plate, which is flat, operates at a temperature of about 140 to 160 degrees centigrade, and contacts the films for 1 to 2 seconds and with a force of 8 to 30kg/cm², preferably 10 to 20kg/cm². The raised flanges surrounding each cavity ensures that the films are sealed together along the flange to form a continuous closed seal. The radiussed edge of each cavity is at least partly formed by a resiliently deformable material, such as for example silicone rubber. This results in reduced force being applied at the inner edge of the sealing flange to avoid heat/pressure damage to the film.

Once sealed, the packages formed are separated from the web of sheet film using cutting means. At this stage it is possible to release the vacuum on the die, and eject the formed packages from the forming die. In this way the packages are formed, filled and sealed while nesting in the forming die. In addition they may be cut while in the forming die as well.

During the forming, filling and sealing steps of the process, the relative humidity of the atmosphere is controlled at ca. 50%. This is done to maintain the heat sealing characteristics of the film. When handling thinner films, it may be necessary to reduce the relative humidity to ensure that the films have a relatively low degree of plasticisation and as such tend to be stiffer resulting in easier handling. The actual specific RH of the atmosphere needed will vary according to the temperature of the environment and the type of film used, however for

- 9 -

temperatures in the region of 20 degrees C, the RH should be in the region of 30 to 50% depending on the thickness and elasticity of the film.

- 5 The invention is not limited to the embodiments hereinbefore described which may be varied in both construction, detail and process step without departing from the spirit of the invention.

- 10 -

CLAIMS

1. A process for producing a thermoformed package comprising the steps of:-
- 5
- placing a first sheet of film over a forming die having at least one cavity;
 - heating the film;

10

 - moulding the film into the at least one cavity thereby forming at least one recess in the film;
 - placing composition in the at least one formed recess; and

15

 - sealing a second sheet of film across the at least one formed recess to produce at least one closed package,
- 20
- the process being characterised in that, once formed, the or each recess is substantially retained in its formed orientation by the application of a vacuum through the or each cavity.
- 25
2. A process as claimed in claim 1 in which the vacuum is maintained at least until completion of the sealing step.
- 30
3. A process as claimed in claims 1 or 2 in which the vacuum is applied through at least one aperture in the forming cavity.

- 11 -

4. A process as claimed in claim 3 in which the or each forming cavity includes a plurality of apertures through which the vacuum is applied
- 5 5. A package obtainable by the process of claims 1 to 4.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/01943

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B65B11/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B65B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DE 93 03 456 U (MOSHEER) 29 April 1993 (1993-04-29) page 2, line 29 -page 4, line 20; figures 1-3	1-5
Y	GB 989 350 A (PROCTER & GAMBLE) 14 April 1965 (1965-04-14) page 3, line 21 - line 47; figures 1-3	1-5

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the International filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the International filing date but later than the priority date claimed

"T" later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the International search

26 May 2000

Date of mailing of the International search report

16/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Claeys, H

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/01943

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 9303456	U	29-04-1993	NONE
GB 989350	A		NONE

THIS PAGE BLANK (USPTO)